


**XPERT HIGH GLOSS** is a high performance, self-adhesive, clear-coated aliphatic polyurethane film designed to protect automotive paint, and other surfaces, from harmful effects of stone chips and abrasion. It has exceptional elongation properties for ease of application which allows for single piece installations. **XPERT HIGH GLOSS** is a very low surface energy film designed to resist staining and offers superior environmental resistance and gloss retention. The clear coat employs special elastomeric polymers that allow scratches in the surface to "heal" over time, eliminating the need for frequent polishing to maintain a just installed appearance. **XPERT HIGH GLOSS** is coated with ultra-clear high performance acrylic adhesive which has excellent adhesion on a broad range of surfaces, while resisting disturbances during installation. This high performance acrylic adhesive is formulated to resist delamination, will not damage paint or leave behind residue upon removal post installation.

## PRODUCT CONSTRUCTION



## GENERAL CHARACTERISTICS

PROPERTIES	TYPICAL VALUES	TESTING CONDITIONS	STANDARDS USED
<b>Peel Adhesion</b>	>4 N/cm >7 N/cm >7 N/cm >7 N/cm >7 N/cm	20 min. @ Room Temperature 72 hr @ Room Temperature 168 hr @ 70°C (158°F) 168 hr @ 35°C (95°F) and 100% Relative Humidity After Xenon Weathering	PSTC 101
<b>Gloss</b>	>90 GU	60 Degree	ISO 2813
<b>Aging Tests</b> Heat Age Water Immersion After Xenon weathering Natural Weathering - AZ Natural Weathering - FL	No Detrimental Effect No Detrimental Effect ΔE<2 / 80% Gloss Retention No Detrimental Effect No Detrimental Effect	16 days @ 80°C (176°F) 400 hr @ 40°C (104°F) 4,500 kJ 3 yr @ 45° south-facing exposure 3 yr @ 5° south-facing exposure	SAE J2527 SAE J1976 SAE J1976
<b>Stone Chip Resistance - Gravelometer</b>	No Detrimental Effect	4.73 L of gravel shot at 70 psi and -29 °C (-20 °F)	ASTM D3170 SAE J400
<b>Mechanical</b> Strength @ Break Tensile Elongation @ Break Shrinkage	>15 MPa >200% <0.1%	Test rate: 20 in/min (500 mm/min) Test rate: 20 in/min (500 mm/min) After accelerated weathering	ASTM D882 ASTM D882 XQT 111
<b>Stain Resistance</b> Water & Soap Spotting Acid Spotting Gasoline Diesel fuel Motor Oil Lacquer Thinner Enamel Reducer Acetone	No Detrimental Effect No Detrimental Effect	Immerse for 30 min, check after 24 hrs. for change	XQT201 XQT202 XQT204 XQT205 XQT206 XQT208 XQT207 XQT208

**RECOMMENDED SHELF LIFE** - 2 years from date of purchase\*

\*If installing film after recommended shelf-life, re-certification by XPERT is required.

**RECOMMENDED STORAGE CONDITIONS** - 72° F (22° C) @ 50% RH

## TARGET APPLICATIONS


Clear gloss polyurethane for stone chip protection, high wear, and abrasion in the automotive, motorcycle, RV, powersports, bicycle, aircraft, and other transportation markets.



FULL WRAP



Hood



Roof



Partial Hood and Fender



Bumper



Rocker Panels



Trunk Ledge



Door Edge



A-Pillars/Roofline